



Since 1967

# Technical Data Sheet

## DUROSEAL™ YELLOW PRIMER

### PORE SEALING PRIMER FOR DUROSEAL™ MEMBRANE SYSTEM

#### PART 1: GENERAL INFORMATION

##### 1.1 PRODUCT DESCRIPTION

DUROSEAL™ YELLOW PRIMER™ is the mandatory penetrating substrates primer with DUROSEAL™ Membrane System in STUCCO-PRO™ (EIFS) SYSTEM.

##### 1.2 BASIC USES

Substrate sealer and adhesion promotes for the adhesion of the DUROSEAL™ membrane.

##### 1.3 ADVANTAGES

Promotes superior adhesion and water moisture intrusion protection:

- Very porous mortar substrates.
- Smooth surfaces.
- Marginally prepared concrete.
- Chalky & Dusty substrates.

#### PART 2: TECHNICAL DATA

PRODUCT CHARACTERISTICS	
COMPOSITION	Water-based rubber.
COLORS	Transparent Yellow
WEIGHT SOLIDS	20.0 ± 2% weight
DENSITY	8.3 lb/gal
VISCOSITY	300 ± 100 cps
pH	8.5 ± 1.0
COVERAGE	100 - 200 ft <sup>2</sup> /gal
DRY TIME	2-12 hrs
SHELF LIFE	12 months

#### PART 3: INSTRUCTIONS

##### 3.1 SURFACE PREPARATION

Check the adherence of unknown substrates, applying the membrane to a small test area before starting work. IMPORTANT: If there is any doubt about the adhesion to the substrate or the type of material it is mandatory

to perform a test before starting work.

Seal all joints, cracks, voids, perimeters, base boards, edges, corners and penetrations with Polyurethane Sealants.

##### 3.2 APPLICATION

DUROSEAL™ YELLOW PRIMER™ It should be mixed gently using an electric drill with mixer before being applied by brush, roller or spray. Primer should never be diluted with water.

Before applying the second layer must be verified to touch the first or wait to dry, at least 1-4 hours. Important: The second layer and subsequent layers must be applied between 2 to 24 hours after application of the first to achieve optimal adhesion between the layers ("intercoat adhesion").

It requires a minimum thickness of DUROSEAL™ YELLOW PRIMER™, Applied at 100 - 200 ft<sup>2</sup> per gallon. To seal the porosity of the concrete and provide an effective barrier against water.

The product should be applied in two or three crossed coats at right angles to reach the minimum thickness specified layers.

Apply detail coat DUROSEAL™ YELLOW PRIMER™ over joints, cracks, sealed perimeter, critical areas and all Polyurethane Sealants pre-sealed areas.

##### 3.3 CLEANUP

Immediately wash hands and tools promptly with water before material hardens. Cured material must be mechanically removed.

##### 3.4 STORAGE AND SHELF LIFE

Do not store DUROSEAL™ YELLOW PRIMER™ where it is likely to freeze or be exposed to hot/cold temperature cycling. Store in a covered area, with a normal 50- 90°F ambient temperature away from excessive heat.

#### PART 4: PRECAUTIONS

Keep out of the reach of children. Children can fall into open buckets and drown. Keep containers tightly closed. Carefully read and follow all cautions and warnings on product label. Avoid release to the environment. Do not breathe mist/vapor/spray. Wash hands thoroughly after handling. Do not eat, drink or smoke when using this product. Use only outdoors or in well-ventilated area. Read SDS before use.

Edition Date: April 29, 2015

©2014 Bull-Bond All rights reserved.

Check our website for the latest version of the Technical Data Sheet



Road PR-175 Km. 0.2 Rio Cañas  
Industrial Park Lot #35  
Caguas, PR 00725

Tel: 787-653-4900  
Fax: 787-653-4949  
email: info@conspro.com  
www.bullbond.com



bullbond.com